

Specifications of Special Pitch (High Soft. Point Pitch) :

SL. NO.	TEST PARAMETERS	UNIT	TEST METHOD	SPECIAL PITCH SPECIFICATIONS
1	Softening Point (Mettler)	°C	ASTM D-3107-87	120-170
2	Toluene Insoluble	%	ASTM D-4312	30 min.
3	Quinolene Insoluble	%	ASTM D-2318-86	5 - 20
4	Coking Value	%	ASTM D-2416-84	55.0 min
5	ASH	%	ASTM D-2415-66	0.5 max