

## **Specifications of Wash Oil (Use as Wood Preservative) :**

ITEM NO.	PROPERTIES	UNIT	TEST METHODS	RANGE	
				Min.	Max.
1	Liquidity Temperature at which the product is completely liquid, after 2h, °C	°C	BS 144	32	~
2	Density, at 38° C & 20°C	kg/l	IS-218-1993	0.935	1.091
3	Distillation up to 205°C	%(m/m)	BS 144	~	5.0
4	Flash Point, closed cup	°C	BS 144	66	~
5	Viscosity, kinematics at 40°C	mm <sup>2</sup> /s	BS 144	4	14
6	Water Content	V/m	IS-218-1993	0.32	~
7	Tar Acid	%	BS 144	6	20
8	Insoluble matter content	%(m/m)	IS-218-1993	0.5	~
9	Saturated Hydrocarbon content	%(m/m)	BS 144	15	~
10	Naphthalene content( By GC)	%(m/m)	BS 144	8	25